

#### Mobil Jet Oil 254

Aviation Exxonmobil, United States

Aircraft-Type Gas Turbine Lubricant

### **Product Description**

Mobil Jet Oil 254 is a third-generation, extra high performance, synthetic aircraft-type gas turbine lubricant engineered to meet the performance requirements for gas turbine engines used in commercial and military aircraft. This product is formulated from a specially prepared, hindered-ester base stock and fortified with a unique chemical additive package. The result is a product having superior thermal and oxidation stability that resists deterioration and deposit formation while maintaining the physical characteristics required by builder and military specifications. The physical properties of Mobil Jet Oil 254 are similar to those currently available, earlier-generation gas turbine lubricants. The effective operating range of the lubricant is between -40°C (-40 °F) and 232°C (450°F).

#### **Features and Benefits**

Mobil Jet Oil 254 is formulated to meet the demanding requirements of latest technology aircraft-type gas turbines operating over a wide range of severe operating conditions. When compared to a typical Type II lubricant, Mobil Jet Oil 254 reduces bulk oil oxidation by up to 50 percent and shows deposit control capability 50 F higher. These properties have been confirmed in various laboratory tests including; the Corrosion-Oxidation Stability Test, Alcor Deposition Test, Vapor Phase Coker, Erdco High-Temperature Bearing Test, Ryder Gear and the Mobil Thin Film Oxidation Test. The closely controlled low-temperature viscosity of Mobil Jet Oil 254, along with its low pour point (below -54 °C), ensure good low-temperature fluidity to permit starting and lubrication at temperatures as low as -40 °C. In extensive laboratory testing and in-flight experience, Mobil Jet Oil 254 also exhibits excellent bulk oil stability at temperatures up to 232 °C (450 °F) for extended periods. The evaporation rate at these temperatures is low enough to prevent excessive loss of volume. The load-carrying ability of Mobil Jet Oil 254 comes from its synthetic base stock viscosity and, therefore, is not subject to loss from viscosity index additive shear. The lubricant has excellent resistance to foaming.Key features and benefits include:

| Features                                  | Advantages and Potential Benefits   |  |
|---|---|--|
| Excellent thermal and oxidation stability | Reduces the formation of carbon and sludge deposits  Maintains engine efficiency and extends engine life  Reduces bulk oil oxidation by 50% and increases deposit control by  50 °F |  |
| Excellent wear and corrosion protection   | Extends seal, gear and bearing life Reduces engine maintenance  |  |

| Features  | Advantages and Potential Benefits  |  |
|---|--|--|
| Viscosity and shear stability across wide temperature range | Provides effective lubrication at high operating temperatures  |  |
| Chemically stable at high operating temperatures            | Reduces evaporation losses and lowers oil consumption  |  |
| Excellent resistance to foaming                             | Maintains film strength under rigorous operating conditions  |  |
| (tood low temperature fluidity                              | Permits start-up and ensures effective lubrication of critical components at temperatures as low as -40 °F |  |

### **Applications**

Mobil Jet Oil 254 is recommended for aircraft gas turbine engines of the turbo-jet, turbo-fan, turbo-prop, and turbo-shaft (helicopter) types used in commercial and military service. It is also suitable for aircraft-type gas turbine engines used in industrial or marine applications. Mobil Jet Oil 254 is approved against the High Thermal Stability (HTS) classification of U.S. Military Specification MIL-PRF-23699. It is also compatible with other synthetic gas turbine lubricants meeting MIL-PRF-23699. However, mixing with other products is not recommended because the blend would result in some loss of the superior performance characteristics of Mobil Jet Oil 254. Mobil Jet Oil 254 is completely compatible with all metals used in gas turbine construction, as well as with F Rubber (Viton A), H Rubber (Buna N), and other commonly used seal materials.

## **Specifications and Approvals**

| Mobil Jet Oil 254 has the following builder approvals                                |   |
|--|---|
| Engines  |   |
| -Honeywell/Lycoming-Turbines   | X |
| -Rolls-Royce/Allison Engine Company  | X |
| -CFM International   | X |
| -General Electric Company  | X |
| -International Aero Engines  | X |
| -Pratt and Whitney Group   | X |
| -Pratt and Whitney, Canada   | X |
| -Rolls-Royce Limited   | X |
| -SNECMA  | X |
| -Honeywell/Garrett Turbine Engine Company  | X |
| Accessories  |   |
| -Honeywell-Auxiliary power units and air cycle machines                              | X |
| -Hamilton Standard-Starters  | X |
| -Hamilton Sundstrand CorpAPUs, constant-speed drives and integrated-drive generators | X |

| Mobil Jet Oil 254  |   |
|--|---|
| Approved against U.S. Military Specification Mil-PRF-23699F High Thermal Stability (HTS) | X |

| Mobil Jet Oil 254  |   |  |
|--------------------|---|--|
| PRI-QPL-AS5780/HPC | X |  |

# **Typical Properties**

| Viscosity  |            |
|--|------------|
| cSt @ 40°C (102 °F)  | 26.4       |
| cSt @ 100°C (212 °F)   | 5.3        |
| cSt @ -40 C (-40 °F)   | 11,500     |
| % change @ -40 C after 72 hours                                  | -2.2       |
| Pour Point, °C (°F), ASTM D 97                                   | -62 (-80)  |
| Flash Point, °C (°F), ASTM D 92                                  | 254 (489)  |
| Fire Point, °C (°F)  | 288 (550)  |
| Autogenous Ignition Temp, °C (°F)                                | 399 (750)  |
| TAN (mg KOH/g sample)  | 0.08       |
| Specific Gravity   | 1.0044     |
| Evaporation Loss, %  |            |
| Evaporation Loss, % 6.5 hr @ 204 °C, 29.5"Hg                     | 2.1,       |
| 6.5 hr @ 232 °C, 29.5" Hg  | 7.4,       |
| 6.5 hr @ 232 °C, 5.5" Hg (Equals pressure @ 40,000 Ft. altitude) | 25.2       |
| Foam, ml   |            |
| Sequence I, 24 °C  | 0          |
| Sequence II, 93.5 °C   | 10         |
| Sequence III, 75 °C (after 200 F test)                           | 0          |
| Foam Stability, after 1 min settling, ml                         | 0          |
| Rubber Swell   |            |
| F Rubber, 72 hr @ 204 °C, %                                      | 20.8       |
| H Rubber, 72 hr @ 70 °C, %                                       | 20.0       |
| Sonic Shear Stability, KV @ 40 C, change, %                      | 0.7        |
| Ryder Gear, average lb/in % Hercolube A                          | 2,715 ,114 |

# **Health and Safety**

Based on available toxicological information, this product is not expected to produce adverse effects on health when used and handled properly. Information on use and handling, as well as health and safety information, can be found in the Material Safety Data Sheet (MSDS) which can be obtained from your local distributor or via the Internet on http://www.exxonmobil.com/lubes.

The ExxonMobil logotype and Mobil are trademarks of Exxon Mobil Corporation, or one of its subsidiaries. PDSAV-04

04-2016

Exxon Mobil Corporation 22777 Springwoods Village Parkway Spring TX 77389

For additional technical information or to identify the nearest U.S. ExxonMobil supply source, call 1800 662-4525.

http://www.exxonmobil.com

Due to continual product research and development, the information contained herein is subject to change without notification. Typical Properties may vary slightly.

© Copyright 2003-2017 Exxon Mobil Corporation. All Rights Reserved.